

HS-AC

GRANULAR ACTIVATED CARBON

APPLICATIONS	
Odor Control	
Paper & Pulp	
Refineries	
Airports	/
Industrial & Commercial	
Museums	
Construction Sites	
Process Treatment Faciliti	es

Hydrosil's HS-AC granular activated carbon (GAC) is derived from a variety of raw materials such as coconut, wood, and coal. Hydrosil's HS-AC is virgin coconut shell activated carbon that is steam activated. The HS-AC is a hard, highly active, low ash content activated carbon.

The HS-AC uses its' unique pore structure to adsorb a wide range or air contaminates in applications such as gas processing, landfills, odor control, volatile organic compound (VOC) treatment, and industrial plants.

TYPICAL PHYSICAL PROPERTIES

Apparent Density, lb./ft ³	30
Standard Mesh Size	4 x 8
Hardness, Min. %	98.0
lodine Number, mg/gm	1100 - 1200
Ash, Max. %	3.0
CTC, Min	60

DIFFERENTIAL PRESSURE 6x12 4x10 4x8 4x8 4x6 50 50 50 50 Superficial Velocity, ft./min

